

P18732.A07

Application No. 09/613,425

**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Original): An aqueous composition comprising:
  - (A) at least one water-soluble component comprising at least one functional group that undergoes a crosslinking reaction;
  - (B) at least one film-forming polymer; and
  - (C) at least one component which provides at least one of moisture barrier properties and/or vapor barrier properties greater than that provided by a combination of components (A) and (B) alone.
2. (Currently Amended): The composition of claim 1 wherein component (A) is ~~selected from~~ comprises at least one of acrylamide-based crosslinkable polymers, polyamidoamine-epihalohydrin resins, polyamines, and or polyimines.
3. (Original): The composition of claim 2 wherein component (A) comprises acrylamide-based crosslinkable polymers.
4. (Original): The composition of claim 3 wherein component (A) comprises cationic functionalized polyacrylamides.

P18732.A07

Application No. 09/613,425

5. (Currently Amended): The composition of claim 2 wherein the functional group of component (A) ~~is selected from~~ at least one of epoxy, azetidinium, aldehyde, carboxyl group, acrylate and derivatives thereof, acrylamide and derivatives thereof, ~~and or~~ quaternary amine.
6. (Currently Amended): The composition of claim 5 wherein the functional group of component (A) ~~is selected from~~ comprises at least one of epoxy ~~and or~~ azetidinium.
7. (Canceled)
8. (Currently Amended)      The composition of claim 2 wherein the film-forming polymer ~~is selected from~~ comprises at least one polymer derived from at least one monomer ~~selected from~~ comprising at least one of styrene, dimethylstyrene, vinyltoluene, chloroprene, butadiene, ethylene, acrylamide, acrylonitrile, acrolein, methylacrylate, ethylacrylate, acrylic acid, methacrylic acid, methyl methacrylate, n-butyl acrylate, vinylidene chloride, vinyl ester, vinyl chloride, vinyl acetate, acrylated urethane, hydroxyethyl acrylate, dimethylaminoethyleneacrylate, ~~and or~~ vinyl acetate.
9. (Currently Amended): The composition of claim 2 wherein the film-forming polymer comprises a latex ~~selected from~~ comprising at least one polymer derived from at least one monomer comprising repeating units derived from an alkyl halide having at least one double bond and an alkene, wherein the alkyl halide has from 2 to 12 C atoms, and wherein the alkene has from 2 to 12 C atoms.
10. (Original): The composition of claim 9 wherein the alkyl halide comprises a vinyl halide.

P18732.A07

Application No. 09/613,425

11. (Original): The composition of claim 10 wherein the alkyl halide comprises a vinyl halide and the alkene comprises an olefin.
12. (Canceled)
13. (Canceled)
14. (Canceled)
15. (Currently Amended): The composition of claim 2 wherein component (C) is ~~selected from~~ comprises one of sizing materials, ketene dimers, alkenyl succinic anhydrides, fatty acids, and or wax emulsions.
16. (Original): The composition of claim 15 wherein the sizing material is a ketene dimer compound prepared from fatty acids of from 16 to 22 C atoms.
17. (Canceled)
18. (Currently Amended): The composition of claim 15 wherein the wax emulsion ~~is selected from~~ comprises at least one of slack or microcrystalline wax.
19. (Original): The composition of claim 15 wherein the dry weight ratio of (A) and (B) to (C) is about 99:1 to 1:99.
20. (Canceled)
21. (Previously Presented): The composition of claim 19 wherein the dry weight ratio of (A) and (B) to (C) is about 60:40 to about 30:70.
22. (Original): The composition of claim 15 further comprising a fluoacid.
23. (Original): The composition of claim 19 further comprising a fluoacid.
24. (Original): A substrate coated with a cured composition of claim 1.

P18732.A07

Application No. 09/613,425

25. (Original): A substrate coated with a cured composition of claim 2.
26. (Original): A metal substrate coated with a cured composition of claim 22.
27. (Currently Amended): The metal substrate of claim 26, wherein the fluoacid is ~~selected from~~ comprises at least one of fluotitanic acid ~~and~~ or fluozirconic acid.
28. (Original): The metal substrate of claim 27, wherein the composition has a pH from about 1.5 to about 5.0.
29. (Original): A metal substrate coated with a cured composition of claim 23.
30. (Currently Amended): The metal substrate of claim 29, wherein the fluoacid is ~~selected from~~ comprises at least one of fluotitanic acid ~~and~~ or fluozirconic acid.
31. (Original): The metal substrate of claim 30, wherein the composition has a pH from about 1.5 to about 5.0.
32. (Original): A cellulosic product comprising a cured composition of claim 1.
33. (Original): A cellulosic product comprising a cured composition of claim 2.
34. (Original): A ceiling tile comprising a cured composition of claim 1.
35. (Original): A non-woven product comprising a cured composition of claim 1.
36. (Original): A latex extender comprising a cured composition of claim 1.
37. (Original): A paint comprising a cured composition of claim 1.
38. (Currently Amended): The composition of claim 8 wherein component (C) is ~~selected from~~ comprises one of sizing materials, ketene dimers, alkenyl succinic anhydrides, fatty acids, ~~and~~ or wax emulsions.

P18732.A07

Application No. 09/613,425

39. (Original): The composition of claim 38 wherein the dry weight ratio of (A) and (B) to (C) is about 99:1 to 1:99.
40. (Original): The composition of claim 39, further comprising a fluoacid.
41. (Original): A metal substrate coated with a cured composition of claim 40.
42. (Currently Amended): The metal substrate of claim 41, wherein the fluoacid is ~~selected from~~ comprises at least one of fluotitanic acid ~~and or~~ fluozirconic acid.
43. (Original): The metal substrate of claim 42, wherein the composition has a pH from about 1.5 to about 5.0.
44. (Original): A cellulosic product comprising a cured composition of claim 39.
45. (Original): A latex extender comprising a cured composition of claim 39.
46. (Original): A non-woven product comprising a cured composition of claim 39.
47. (Original): A method of preparing a coated substrate which comprises:
- (1) coating a substrate with a coating composition comprising:

(A) at least one water-soluble component comprising at least one functional group that undergoes a crosslinking reaction; (B) at least one film-forming polymer; and (C) at least one component which provides at least one of moisture barrier properties and/or vapor barrier properties greater than that provided by a combination of components (A) and (B) alone; and
  - (2) curing the coating composition on the substrate.

P18732.A07

Application No. 09/613,425

48. (Currently Amended): The method of claim 47 wherein component (A) is ~~selected from~~ comprises at least one of acrylamide-based crosslinkable polymers, polyamidoamine-epihalohydrin resins, polyamines, and or polyimines.
49. (Original): The method of claim 48 wherein component (A) comprises acrylamide-based crosslinkable polymers.
50. (Original): The method of claim 48 wherein component (A) comprises cationic functionalized polyacrylamides.
51. (Currently Amended): The method of claim 48 wherein the functional group of component (A) is ~~selected from~~ comprises at least one of epoxy, azetidinium, aldehyde, carboxyl group, acrylate and derivatives thereof, acrylamide and derivatives thereof, and or quaternary amine.
52. (Currently Amended): The method of claim 51 wherein the functional group of component (A) is ~~selected from~~ comprises at least one of epoxy and or azetidinium.
53. (Canceled)
54. (Currently Amended): The method of claim 48 wherein the film-forming polymer is ~~selected from~~ comprises at least one polymer derived from at least one monomer ~~selected from~~ comprising at least one of styrene, dimethylstyrene, vinyltoluene, chloroprene, butadiene, ethylene, acrylamide, acrylonitrile, acrolein, methylacrylate, ethylacrylate, acrylic acid, methacrylic acid, methyl methacrylate, n-butyl acrylate, vinylidene chloride, vinyl ester, vinyl chloride, vinyl acetate, acrylated urethane, hydroxyethyl acrylate, dimethylaminoethyleneacrylate, and or vinyl acetate.

P18732.A07

Application No. 09/613,425

55. (Currently Amended): The method of claim 47 wherein the film-forming polymer comprises a latex ~~selected from~~ comprising at least one polymer derived from at least one monomer comprising repeating units derived from an alkyl halide having at least one double bond and an alkene, wherein the alkyl halide has from 2 to 12 C atoms, and wherein the alkene has from 2 to 12 C atoms.

56. (Original): The method of claim 55 wherein the alkyl halide comprises a vinyl halide and the alkene comprises an olefin.

57. (Canceled)

58. (Currently Amended): The method of claim 48 wherein component (C) is ~~selected from~~ comprises one of sizing materials, ketene dimers, alkenyl succinic anhydrides, fatty acids, ~~and~~ or wax emulsions.

59. (Original): The method of claim 58 wherein the sizing material is a ketene dimer compound prepared from fatty acids having C<sub>16</sub> to C<sub>22</sub>.

60. (Original): The method of claim 58 wherein the dry weight ratio of (A) and (B) to (C) is about 99:1 to 1:99.

61. (Original): The method of claim 60 wherein the dry weight ratio of (A) and (B) to (C) is about 60:40 to 30:70.

62. (Original): The method of claim 58 further comprising a fluoacid.

63. (Original): The method of claim 60 further comprising a fluoacid.

64. (Original): A metal substrate prepared by the method of claim 62.

P18732.A07

Application No. 09/613,425

65. (Currently Amended): The metal substrate of claim 64, wherein the fluoacid is ~~selected from~~ comprises at least one of fluotitanic acid and or fluozirconic acid.

66. (Original): The metal substrate of claim 65 wherein the composition has a pH from about 1.5 to about 5.0.

67. (Original): A metal substrate prepared by the method of claim 63.

68. (Currently Amended): The metal substrate of claim 67, wherein the fluoacid is ~~selected from~~ comprises at least one of fluotitanic acid and fluozirconic acid.

69. (Original): The metal substrate of claim 68, wherein the composition has a pH from about 1.5 to about 5.0.

70. (Currently Amended): The method of claim 50 wherein the film-forming polymer is ~~selected from~~ comprises at least one polymer derived from monomers of alkyl halides of from 2-12 C atoms, alkene halides of from 2-12 C atoms, alkyl acrylamides of from 2-12 C atoms, alkene acrylamides of from 2-12 C atoms, alkyl acrylates of from 2-12 C atoms, and or alkene acrylates of from 2-12 C atoms.

71. (Currently Amended): The method of claim 70 wherein component (C) is ~~selected from~~ comprises one of sizing materials, ketene dimers, alkenyl succinic anhydrides, fatty acids, and or wax emulsions.

72. (Canceled)

73. (Canceled)

74. (Canceled)

75. (Canceled)



P18732.A07

Application No. 09/613,425

76. (Canceled)

77. (Currently Amended): A method of preparing cellulosic products which comprises:

(1) substantially simultaneously or sequentially adding a composition to a system comprising cellulosic fibers,

wherein the system ~~is selected from~~ comprises at least one of aqueous system, felt, web, and or combinations thereof,

the composition comprising:

(A) at least one water-soluble component comprising at least one functional group that undergoes a crosslinking reaction; (B) at least one film-forming polymer; and (C) at least one component which provides at least one of moisture barrier properties and/or vapor barrier properties greater than that provided by a combination of components (A) and (B) alone.

78. (Currently Amended): The method of claim 77 wherein component (A) is ~~selected from~~ comprises at least one of acrylamide-based crosslinkable polymers, polyamidoamine-epihalohydrin resins, polyamines, and or polyimines.

79. (Original): The method of claim 78 wherein component (A) comprises acrylamide-based crosslinkable polymers.

80. (Original): The method of claim 79 wherein component (A) comprises cationic functionalized polyacrylamides.

P18732.A07

Application No. 09/613,425

81. (Currently Amended): The method of claim 78 wherein the functional group of component (A) ~~is selected from~~ comprises at least one of epoxy, azetidinium, aldehyde, carboxyl group, acrylate and derivatives thereof, acrylamide and derivatives thereof, ~~and or~~ quaternary amine.

82. (Currently Amended): The method of claim 81 wherein the functional group of component (A) ~~is selected from~~ comprises at least one of epoxy ~~and or~~ azetidinium.

83. (Canceled)

84. (Currently Amended): The method of claim 78 wherein the film-forming polymer ~~is selected from~~ comprises at least one polymer derived from at least one monomer ~~selected from~~ comprising at least one of styrene, dimethylstyrene, vinyltoluene, chloroprene, butadiene, ethylene, acrylamide, acrylonitrile, acrolein, methylacrylate, ethylacrylate, acrylic acid, methacrylic acid, methyl methacrylate, n-butyl acrylate, vinylidene chloride, vinyl ester, vinyl chloride, vinyl acetate, acrylated urethane, hydroxyethyl acrylate, dimethylaminoethyleneacrylate, ~~and or~~ vinyl acetate.

85. (Currently Amended): The method of claim 78 wherein the film-forming polymer comprises a latex ~~selected from~~ comprising at least one polymer derived from at least one monomer comprising repeating units derived from an alkyl halide having at least one double bond and an alkene, wherein the alkyl halide has from 2 to 12 C atoms, and wherein the alkene has from 2 to 12 C atoms.

86. (Original): The method of claim 85 wherein the alkyl halide comprises a vinyl halide and the alkene comprises an olefin.

P18732.A07

Application No. 09/613,425

87. (Canceled)

88. (Currently Amended): The method of claim 78 wherein component (C) is ~~selected from~~ comprises one of sizing materials, alkenyl succinic anhydrides, fatty acids, ~~and~~ or wax emulsions.

89. (Original): The method of claim 88 wherein the sizing material is a ketene dimer compound prepared from fatty acids of from 16 to 22 C atoms.

90. (Original): The method of claim 88 wherein the dry weight ratio of (A) and (B) to (C) is about 99:1 to 1:99.

91. (Original): The method of claim 90 wherein the dry weight ratio of (A) and (B) to (C) is about 60:40 to 30:70.

92. (Currently Amended): The method of claim 80 wherein the film-forming polymer is ~~selected from~~ comprises at least one polymer derived from monomers of alkyl halides of from 2-12 C atoms, alkene halides of from 2-12 C atoms, alkyl acrylamides of from 2-12 C atoms, alkene acrylamides of from 2-12 C atoms, alkyl acrylates of from 2-12 C atoms, ~~and~~ or alkene acrylates of from 2-12 C atoms.

93. (Currently Amended): The method of claim 92 wherein component (C) is ~~selected from~~ comprises one of sizing materials, alkenyl succinic anhydrides, fatty acids, ~~and~~ or wax emulsions.

94. (Original): The method of claim 92 wherein the dry weight ratio of (A) and (B) to (C) is about 60:40 to 30:70.

95. (Original): A cellulosic product prepared by the method of claim 94.

P18732.A07

Application No. 09/613,425

96. (Currently Amended): ~~A ceiling~~ A ceiling tile prepared by the method of claim 94.

97. (Original): A non-woven product prepared by the method of claim 94.

98. (Original): A method for forming a substantially chromium-free, dried in place conversion coating on a metal surface comprising applying to a metal surface:

(1) an aqueous composition comprising (A) at least one water-soluble component comprising at least one functional group that undergoes a crosslinking reaction; (B) at least one film-forming polymer; and (C) at least one component which provides at least one of moisture barrier properties and/or vapor barrier properties greater than that provided by a combination of components (A) and (B) alone; and

(2) fluoacid,

wherein the amount of the composition in (1) is from about 0.1 to about 90% by weight, and

wherein the amount of fluoacid is from about 0.2 to about 20% by weight.

99. (Original): The method of claim 98 wherein said coating composition is dried in place on surface of said substrate.

100. (Original): The method of claim 98 further comprises rinsing said coating composition from said coated substrate.

101. (Currently Amended): The method of claim 98, wherein the fluoacid ~~is selected from~~ comprises at least one of fluotitanic acid ~~and or~~ fluozirconic acid.

P18732.A06

Appl. No. 09/613,425

102. (Original): The method of claim 101, wherein the composition has a pH from about 1.5 to about 5.0.

103. (Currently Amended): The method of claim 102 wherein component (A) ~~is selected from~~ comprises at least one of acrylamide-based crosslinkable polymers, polyamidoamine-epihalohydrin resins, polyamines, ~~and~~ or polyimines.

104. (Original): The method of claim 103 wherein component (A) comprises acrylamide-based crosslinkable polymers.

105. (Currently Amended): The method of claim 103 wherein the functional group of component (A) ~~is selected from~~ comprises at least one of epoxy, azetidinium, aldehyde, carboxyl group, acrylate and derivatives thereof, acrylamide and modification thereof, ~~and~~ or quaternary amine.

106. (Currently Amended): The method of claim 105 wherein the functional group of component (A) ~~is selected from~~ comprises at least one of epoxy ~~and~~ or azetidinium.

107. (Canceled)

108. (Currently Amended): The method of claim 103 wherein the film-forming polymer is ~~selected from~~ comprises at least one polymer derived from at least one monomer ~~selected from~~ comprising at least one of styrene, dimethylstyrene, vinyltoluene, chloroprene, butadiene, ethylene, acrylamide, acrylonitrile, acrolein, methylacrylate, ethylacrylate, acrylic acid, methacrylic acid, methyl methacrylate, n-butyl acrylate, vinylidene chloride, vinyl ester, vinyl chloride, vinyl acetate, acrylated urethane, hydroxyethyl acrylate, dimethylaminoethyleneacrylate, ~~and~~ or vinyl acetate.

P18732.A06

Appl. No. 09/613,425

109. (Currently Amended): The method of claim 101 wherein the film-forming polymer comprises a latex ~~selected from~~ comprising at least one polymer comprising repeating units derived from an alkyl halide having at least one double bond and an alkene, wherein the alkyl halide has from 2 to 12 C atoms, and wherein the alkene has from 2 to 12 C atoms.

110. (Currently Amended): The method of claim 103 wherein component (C) is a polymer ~~selected from~~ comprising one of sizing materials, alkenyl succinic anhydrides, fatty acids, and or wax emulsions.

111. (Original): The method of claim 110 wherein the sizing material is a ketene dimer compound prepared from fatty acids of from 16 to 22 C atoms.

112. (Original): The method of claim 110 wherein the dry weight ratio of (A) and (B) to (C) is about 99:1 to 1:99.

113. (Original): The method of claim 112 wherein the dry weight ratio of (A) and (B) to (C) is about 60:40 to 30:70.

114. (Original): A metal substrate prepared by the method of claim 98.

115. (Original): A metal substrate prepared by the method of claim 103.

116. (Canceled)

117. (Original): A metal substrate coated by the method of claim 109.

118. (Original): A metal substrate coated by the method of claim 112.